

DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
------------	--------	----------------

INDIANSUMMER 101

Lightfastness:	2 - 3	54004
----------------	-------	-------

Possible color change:



Abrasion values:	Level:	
Dry	5	53339
Wet	3	
Perspiration	3	

Permanent folding behavior: 20.000 bucklings	passed	53340
---	--------	-------

Tensile strength: 20 N/mm	passed	53329
------------------------------	--------	-------

Burning behavior: EN1021 part I u. II	passed	
--	--------	--

Detailed information about light fastness, abrasion values, skin tolerance and burning behaviour can be found at:
www.vegetable-tanned-leather.com/data-and-facts.html

Tested for
Heavy metals, aniline,
(Conducted by the German Institute of Environment in Bremen, 2013)



Color: Indiansummer 101
Collection: Velour
Thickness: 1,4 - 1,6 mm



* Valid only for skins from eco farming
(Please ask for availability)

DATA SHEET



Results of the examination for aniline

Parameter	H 8235 FL-2 Ecopell 101 Indiansummer KW 45 (mg/kg)	NG (mg/kg)	Requirements IVN Leather (mg/kg)
Aniline	10	5	60*

* Sum limit for further amines going beyond European legislation
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylenediamine and Aniline)

Results of the examination for heavy metals

Heavy metals	K 2407 FL-4 Ecopell 229 Himbeer KW 40 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<0,5	0,5	1
Aluminium	20	10	500
Arsenic	<0,5	0,5	1
Lead	<0,5	0,5	1
Cadmium	<0,2	0,2	0,2
Chrome	12	1	50
Cobalt	<1	1	5
Mercury	<0,1	0,1	0,2
Nickel	<1	1	5
Titanium	<10	10	500
Zirconium	<5	5	500

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected