

# DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
------------	--------	----------------

LAVANDULA 007

Lightfastness: 5 54004

Possible color change:



Abrasion values:	Level:	
Dry	2 - 3	53339
Wet	2 - 3	
Perspiration	2	

Permanent folding behavior:  
20.000 bucklings passed 53340

Tensile strength:  
20 N/mm passed 53329

Burning behavior:  
EN1021 part I u. II passed

Detailed information about light fastness, abrasion values, skin tolerance and burning behaviour can be found at:  
[www.vegetable-tanned-leather.com/data-and-facts.html](http://www.vegetable-tanned-leather.com/data-and-facts.html)

Tested for  
Heavy metals, aniline  
(Conducted by the German Institute of Environment in Bremen, 2013/2016)



Color: Lavandula 007  
Collection: Velour  
Thickness: 1,4 - 1,6 mm



\* Valid only for skins from eco farming  
(Please ask for availability)

# DATA SHEET



## Results of the examination for aniline

Parameter	H 8252 FL-2 Ecopell 007 Lavandula KW 46 (mg/kg)	NG (mg/kg)	Requirements IVN Leather (mg/kg)
Aniline	nn	3	≤ 60*

\* Sum limit for further amines going beyond European legislation  
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylenediamine and Aniline)

## Results of the examination for heavy metals

Heavy metals	H 8252 FL-2 Ecopell 007 Lavandula KW 46 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)	Requirements ECARF (mg/kg)
Antimony	<0,5	0,5	1	-
Aluminium	90	10	500	-
Arsenic	<0,5	0,5	1	-
Lead	<0,5	0,5	1	-
Cadmium	<0,2	0,2	0,2	-
Chrome	9	1	50	40
Cobalt	<1	1	5	-
Mercury	<0,1	0,1	0,2	-
Nickel	<1	1	5	-
Titanium	<10	10	500	-
Zirconium	<5	5	500	-

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected