



DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	1	54004
Possible color change:		
Abrasion values:	Level:	
Dry	5	53339
Wet	4 - 5	
Perspiration	3 - 4	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329
Burning behavior: y EN1021 part I u. II	passed	

PALOMA 704



Color: Paloma 704
Collection: Nappa
Thickness: 1,4 - 1,6 mm

Detailed information about light fastness, abrasion values, skin tolerance and burning behaviour can be found at:
www.vegetable-tanned-leather.com/data-and-facts.html