

DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	5	54004
Abrasion values:	Level:	
Dry	5	53339
Wet	3 - 4	
Perspiration	2 - 3	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329
SG-Test:	passed	
Burning behavior: EN1021 part I u. II	passed	

BUNNY 330



Color: Bunny 330
Collection: Rodeo
Thickness: 1,4 - 1,6 mm



Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at:
www.vegetable-tanned-leather.com/data-and-facts.html

Tested for

Heavy metals, aniline, p-Phenylendiamin
(Conducted by the German Institute of Environment in Bremen, 2017)

DATA SHEET



Results of the examination for aniline

Parameter	K 4775 FL - 2 Ecopell 330 Bunny KW 11 (mg/kg)	NG (mg/kg)	Requirements IVN Leather (mg/kg)	Requirements ECARF (mg/kg)
Aniline	nn	5	≤ 60*	-
p-Phenylendiamin	nn	5	≤ 60*	5

* Sum limit for further amines going beyond European legislation
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylendiamine and Aniline)

Results of the examination for heavy metals

Heavy metals	K 4775 FL - 2 Ecopell 330 Bunny KW 11 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)	Requirements ECARF (mg/kg)
Antimony	<0,5	0,5	≤ 1	-
Aluminium	120	10	≤ 500	-
Arsenic	<0,5	0,5	≤ 1	-
Lead	1	0,5	≤ 1	-
Cadmium	<0,2	0,2	≤ 0,2	-
Chrome	16	1	≤ 50	40
Cobalt	<1	1	≤ 5	-
Mercury	<0,2	0,2	≤ 0,2	-
Nickel	<1	1	≤ 5	-
Titanium	<10	10	≤ 500	-
Zirconium	<5	5	≤ 500	-

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected