

DATA SHEET



Results of the examination for aniline

| Parameter | H 8235 FL-1 Ecopell 844 Calvados KW 45 (mg/kg) | NG (mg/kg) | Requirements IVN Leather (mg/kg) |
|-----------|---|---------------|--|
| Aniline | 12 | 5 | ≤ 60* |

* Sum limit for further amines going beyond European legislation
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylenediamine and Aniline)

Results of the examination for heavy metals

| Heavy metals | H 8235 FL-1 Ecopell 844 Calvados KW 45 (mg/kg) | BG (mg/kg) | Requirements IVN Leather (mg/kg) |
|--------------|---|---------------|--|
| Antimony | <0,5 | 0,5 | 1 |
| Aluminium | 30 | 10 | 500 |
| Arsenic | <0,5 | 0,5 | 1 |
| Lead | <0,5 | 0,5 | 1 |
| Cadmium | <0,2 | 0,2 | 0,2 |
| Chrome | 17 | 1 | 50 |
| Cobalt | <1 | 1 | 5 |
| Mercury | <0,1 | 0,1 | 0,2 |
| Nickel | <1 | 1 | 5 |
| Titanium | <10 | 10 | 500 |
| Zirconium | <5 | 5 | 500 |

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected