

DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	3 - 4	54004
Abrasion values:	Level:	
Dry	3 - 4	53339
Wet	3	
Perspiration	2 - 3	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329
SG-Test:	passed	
Burning behavior: EN1021 part I u. II	passed	

COAL 100



Color: Coal 100
Collection: Rodeo
Thickness: 1,4 - 1,6 mm



Detailed information about light fastness, abrasion values, skin tolerance and burning behaviour can be found at:
www.vegetable-tanned-leather.com/data-and-facts.html

Tested for
Heavy metals
(Conducted by the German Institute of Environment in Bremen, 2014)

DATA SHEET



Results of the examination for heavy metals

Heavy metals	H 9543 FL-2 Ecopell 100 Coal KW 38 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)	Requirements ECARF (mg/kg)
Antimony	<0,5	0,5	1	-
Aluminium	0	10	500	-
Arsenic	<0,5	0,5	1	-
Lead	<0,5	0,5	1	-
Cadmium	<0,2	0,2	0,2	-
Chrome	28	1	50	40
Cobalt	<1	1	5	-
Mercury	<0,2	0,1	0,2	-
Nickel	<1	1	5	-
Titanium	<10	10	500	-
Zirconium	<5	5	500	-

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected